

Soudafoam TT

Revision: 3/04/2023

Page 1 from 2

Technical data

Basis	Polyurethane
Consistency	Stable foam, thixotropic
Curing system	Moisture curing
Skin Formation (EN 17333-3)	8 min
Cutting Time (EN 17333-3)	30 min
Free foamed density (EN 17333-1)	Ca. 29 kg/m ³
Thermal conductivity (EN 17333-5)	29,7 mW/m.K
Box Yield (EN 17333-1)	750 ml yields ca. 29 l of foam
Joint Yield (EN 17333-1)	750 ml yields ca. 20 m of foam
Expansion during curing (EN 17333-2)	Ca. 141 %
Percentage closed cells (ISO4590)	Ca. 7 %
Water absorption (EN 29767)	Ca. 0,23 kg/m ²
Reaction to fire classification (EN 13501-1)	No fire classification (F)
Compressive strength (EN 17333-4)	Ca. 21 kPa
Shear strength (EN 17333-4)	Ca. 52 kPa
Tensile Strength (EN 17333-4)	Ca. 77 kPa
Elongation at Fmax (EN 17333-4)	Ca. 14,7 %
Temperature resistance**	-40 °C till +90 °C (cured)

** This information relates to fully cured product.

Product description

Soudafoam TT is a one-component, self-expanding, ready to use PU-foam, which contains HCFC- and CFC-free propellants who are not harmful for the ozonlayer.

Properties

- Easy and fast to apply (saving of up to 30 % in labour time).
- Good adhesion on all surfaces (except PE, PP and PTFE).
- Replaces mortar. Cheaper than the traditional systems.
- Very good bonding properties.
- Fast curing
- Very precise to dose.
- Does not age or rot, but should not be exposed to UV radiation.
- Extremely light
- Resistant to cold and heat
- Resistant to wind forces
- Freon free (not harmless to ozone layer and greenhouse effect)

Applications

- Installation and repair of roof tiles
- Filling of cavities.
- Sealing of all openings in roof constructions.
- Apply of an acoustic baffle

Packaging

Colour: grey, terracotta

Packaging: 750 ml aerosol (net)

Shelf life

18 months unopened and stored in dry and cool conditions (Between 5 and 25 °C), Upright storage is recommended.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Soudafoam TT

Revision: 3/04/2023

Page 2 from 2

Application method

Shake the can at least for 20 seconds. Put the adapter on the valve. Substrate needs to be free of dust and grease. Apply glue in strands with a thickness of ± 3 cm. Fill the joint for $\frac{2}{3}$ as the foam will expand further during curing. Shake regularly during application. Immediately remove spilled foam with a foam cleaner, cured foam must be removed mechanically. Prior to using the cleaner, test whether surfaces are affected or not. Especially plastics and lacquer or paint layers can be sensitive to this. Remove the cured PU-foam mechanically as good as possible.

Can temperature: $+5^{\circ}\text{C} - 30^{\circ}\text{C}$

Ambient temperature: $+5^{\circ}\text{C} - 30^{\circ}\text{C}$.

Surface temperature: $+5^{\circ}\text{C} - 35^{\circ}\text{C}$

Health- and Safety Recommendations

Take the usual labour hygiene into account. Always wear gloves and goggles. Remove cured foam mechanically. Never burn away. Consult label and material safety data sheet for more information. When vaporizing (for example with a compressor), additional security measures will be required. Use only in well ventilated areas.

Remarks

- Moisten surfaces with a water sprayer prior to application. If you have to work in layers repeat moistening after each layer. For not common surfaces we recommend an adhesion test.

Standards and certificates

- Resistance to adhesion, according to UNE 83.822.95
- Resistance to freeze-thaw cycles, according to UNE 83.822.95
- Heat resistance, according to UNE 83.822.95

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.