

Silirub WS

Revision: 3/05/2022

Page 1 from 3

Technical data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 6 min
Curing speed * (23°C/50% R.H.)	Ca. 2 mm/24h
Hardness**	Ca. 23 ± 5 Shore A
Density	Ca. 1,14 g/ml
Elastic recovery (ISO 7389)**	> 80 %
Maximum allowed distortion	25 %
Max. tension (ISO 37)**	Ca. 1,60 N/mm ²
Elasticity modulus 100% (ISO 37)**	Ca. 0,39 N/mm ²
Elongation at break (ISO 37)**	> 800 %
Temperature resistance**	-60 °C → 180 °C
Application temperature	5 °C → 35 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Silirub WS is a high-quality, neutral, elastic one-component joint sealant based on fast skinning silicones. Silirub WS has been developed for weather sealing of expansion joints in the façade industry.

Properties

- Compatible with PVB-film
- Compatible with sealants for double glazing based on polysulphides and silicones.
- Very easy to apply
- Permanently elastic after curing
- UV-resistant
- Very good adhesion on many materials
- Excellent moisture resistance
- Neutral curing
- Resistant against UV-radiation, rain, frost, wind, ozone and extreme temperatures
- Excellent adhesion properties on glass, laminated glass, coated aluminium, galvanised steel, concrete and masonry
- Very good resistance to ageing
- Not paintable
- Not suitable for natural stone
- MEKO free

Applications

- Weatherproof sealing of facade elements and in particular glass curtain walls.
- All usual building, connection, expansion and dilatation joints.
- Excellent for double glazing system applications.
- Suitable for weatherproof sealing around structurally glazed window panels.

Packaging

Colour: black

Packaging: 300 ml cartridge, 600 ml foil bag

Shelf life

18 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Chemical resistance

Resistant to intermittent exposure to salt water, detergents, oils, weak acids and bases (preliminary test required). Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Silirub WS

Revision: 3/05/2022

Page 2 from 3

Substrates

Substrates: all usual building substrates, metals, glass

Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Silirub WS has a good adhesion to most substrates. However, for optimal adhesion and in critical applications, such as joints exposed to extreme weather conditions, high- or water-loaded joints, we recommend to follow a pre-treatment procedure. Prepare non-porous surfaces with a Soudal activator or cleaner (see Technical Data Sheet). Porous surfaces should be primed with Primer 150.

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion test on any substrate. Due to the wide variety materials used in façade technology a preliminary compatibility test is necessary.

Joint dimensions

Glazing and window applications: top sealing = minimum width 4 mm, depth at least 6 mm.

Minimum joint width for connection joints around windows: 10 mm. Weatherseal and other applications: joint width 5 - 10 mm: joint depth 5 mm. Joint width 10 - 30 mm: depth = 1/2*width.

Application method

Apply the product by means of a manual-, battery- or pneumatic- caulking gun. Apply Silirub WS evenly without air inclusions into the joint. Smoothen the joint with a spatula with the help of finishing solution. Avoid that soapy solution comes between the joint edges and sealant (to prevent adhesion loss).

Application method: With a manual, pneumatic or accu caulking gun.

Cleaning: Clean with Soudal Surface Cleaner or with Soudal Swipex, immediately after use Cured Silirub WS can only be removed mechanically.

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Dangerous. Respect the precautions for use.

Remarks

- Not suitable as adhesive for structural glazing applications.
- Do not use on natural stones like marble, granite,...(staining). Use Soudal Silirub MA or Silirub+ S8800 for this application.
- The use of Soudal Surface Activator is recommended in combination with powder coated aluminium.
- Discoloration due to chemicals, high temperatures, UV-radiation may occur. A change in color does not affect the technical properties of the product.
- A total absence of UV can cause a color change of the sealant.
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.
- We strongly recommend not to apply the Finishing Solution in full sunlight as it will dry very fast in these circumstances.
- Do not use in applications where continuous water immersion is possible.
- Not suitable for bonding aquariums.
- Do not use on polycarbonate. Use Silirub PC instead.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Silirub WS

Revision: 3/05/2022

Page 3 from 3

Standards and certificates

- Meets ISO 11600 G 25 LM
- Meets ASTM C920 Type S, Grade NS, Class 50, Use T, NT, A and G

Environmental clauses

Leed regulation:

Silirub WS conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.